

Kodak DSII Progressive Lens

Add Range: +0.75 to +3.50 in .25 D steps	Lens Material	Colors	Sphere Range	Cylinder Range to -6.00, limited to a combined sph/cyl power of:	Maximum Cutout	Index of Refraction	Abbe Value	Specific Gravity (gm/ cm ³)
Standard Index	Standard Resin		+4.00 to -8.00	-8.00	80mm	1.499	58	1.32
	*Trivex®		+4.50 to -10.00	-10.00	76mm	1.532	44	1.11
Thin & Light	*Polycarbonate		+5.00 to -10.00	-10.00	78mm	1.586	30	1.20
	*1.60 Index		+6.00 to -11.00	-11.00	76mm	1.594	41	1.30
	*1.67 High Index		+10.00 to -12.00	-12.00	76mm	1.664	31	1.37
	1.74 High Index		+10.00 to -13.25	-13.25	70/75mm	1.735	33	1.46
Photochromic	Transitions® Signature® 1.50	Gray/Brown	+4.00 to -8.00	-8.00	78mm	1.497	58	1.27
	*Transitions Signature Trivex	Gray/Brown	+4.50 to -10.00	-10.00	74mm	1.532	44	1.11
	*Transitions Signature Polycarbonate	Gray/Brown	+5.00 to -10.00	-10.00	75mm	1.586	30	1.20
	*Transitions Signature 1.60	Gray/Brown	+6.00 to -10.00	-10.00	75mm	1.594	41	1.30
	*Transitions Signature 1.67	Gray/Brown	+6.00 to -11.00	-11.00	76mm	1.664	31	1.37
	Transitions Signature 1.74	Gray/Brown	+9.00 to -13.00	-13.00	70/75mm	1.735	33	1.46
Polarized	Polarized 1.50	Gray/Brown	+4.00 to -8.00	-8.00	80mm	1.499	58	1.32
	*Polarized Polycarbonate	Gray/Brown	+5.00 to -10.00	-10.00	78mm	1.586	30	1.20
	*Polarized 1.60	Gray/Brown	+5.75 to -10.00	-10.00	75mm	1.594	41	1.30
	*Polarized 1.67	Gray/Brown	+10.00 to -12.00	-12.00	76mm	1.664	31	1.37

* Recommended for drill mount frames.




 5803 Newton Drive, Suite A
 Carlsbad, CA 92008
 800-759-0075
Signet Armorlite, Inc. www.signetarmorlite.com

See the *Colors* of Life®